



INVESTOR IN PEOPLE


The Patent Office
Concept House
Cardiff Road
Newport
South Wales
NP10 8QQ

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.



Signed

W. Evans


Dated

19 February 2003



11

Patents Act 1977
(Rule 16)



1/77

Request for grant of a patent

(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)

The Patent Office

Cardiff Road

Newport

South Wales

NP16 8QQ

09AUG02 E739839 1 000133
P01/7700 0.00-000000

1. Your reference **84594/12480/05** **025507.2**

2. Patent application number
(The Patent office will fill in this part) **025507.2**

3. Full name, address and postcode of the or of each applicant (underline all surnames)
EASTMAN KODAK COMPANY
343 STATE STREET
ROCHESTER
NEW YORK 14650-2201
UNITED STATES OF AMERICA
0218507.2
423020001

Patents ADP number (if you know it)

If the applicant is a corporate body, give the country/state of its incorporation

NEW JERSEY

4. Title of the invention **A METHOD OF MAKING A MATERIAL**

5. Name of your agent (if you have one) **A FREEMAN**

"Address for service" in the United Kingdom to which all correspondence should be sent (including the postcode)

KODAK LIMITED
PATENTS, W92-3A
HEADSTONE DRIVE
HARROW
MIDDLESEX HA1 4TY

8098650001

Patents ADP number (if you know it)

6. If you are declaring priority from one or more earlier patent applications, give the country and date of filing of the or of each of these earlier applications and (if you know it) the or each application number	Country	Priority application number (if you know it)	Date of Filing (day / month / year)

7. If this application is divided or otherwise derived from an earlier UK application, give the number and the filing date of the earlier application	Number of earlier application	Date of filing (day / month / year)

8. Is a statement of inventorship and of right to grant a patent required in support of this request? (Answer 'Yes' if:
a) any applicant named in part 3 is not an inventor, or
b) there is an inventor who is not named as an applicant, or
c) any named applicant is a corporate body.
See note (d)) **YES**

Patents Form 1/77

9. Enter the number of sheets for any of the following items you are filing with this form. Do not count copies of the same document.

Continuation sheets of this form

Description 8

Claim(s) 2

Abstract 1

Drawing(s)

10. If you are also filing any of the following, state how many against each item.

Priority Documents

Translations of priority documents

Statement of inventorship and right to grant of a patent (*Patents Form 7/77*)

Request for preliminary examination and search (*Patent Form 9/77*)

Request for substantive examination (*Patent Form 10/77*)

Any other documents
(*please specify*)

11.

I/We request the grant of a patent on the basis of this application.

Signature

Date 8 August 2002

12. Name and daytime telephone number of person to contact in the United Kingdom

A FREEMAN

020 8424 4431

Warning

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.

Notes

- If you need help to fill in this form or you have any questions, please contact the Patent Office on 0645 500505.
- Write your answers in capital letters using black ink or you may type them.
- If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.
- If you have answered 'Yes' Patents Form 7/77 will need to be filed.
- Once you have filled in the form you must remember to sign and date it.
- For details of the fee and ways to pay please contact the Patent Office.

A METHOD OF MAKING A MATERIAL

FIELD OF THE INVENTION

The present invention relates to a method of making a material. In particular the invention relates to a method of making a foamed material suitable for use as, amongst other things, an inkjet medium. An example of such a material is that described in our co-pending UK Patent application entitled "Inkjet Recording Medium", having the same filing date as the present application and corresponding to our Docket number 84595.

10

BACKGROUND OF THE INVENTION

Most commercial photo-quality inkjet media can be classified in one of two categories according to whether the principal component material forms a layer that is porous or non-porous in nature. Inkjet media having a porous layer are typically formed of inorganic materials with a polymeric binder. When ink is applied to the medium it is absorbed quickly into the porous layer by capillary action. However, the open nature of the layer can contribute to instability of printed images. Inkjet media having a non-porous layer are typically formed by the coating of one or more polymeric layers onto a support. When ink is applied to such media, the polymeric layers swell and absorb the applied ink. However, due to limitations of the swelling mechanism, this type of media is slow to absorb the ink, but once dry, printed images are often stable when subjected to light and ozone.

A method of manufacturing a material that addresses these problems is required. The applicant has recognised that use of a polymer foam coated on a support would address the problems associated with the inkjet media. A method of manufacturing such a material is required. Although the material when manufactured would be useful as an inkjet media, its use would not be limited in this regard. Indeed, the material may find uses in any number of applications. For example, the material may be used as insulation tape, a coating for e.g. shelves, sticky-backed coating material, and any other possible use for a material.

30

Traditionally, polymer foams are manufactured using mostly hydrophobic thermoplastic materials such as Polyurethane, Polyvinyl Chloride (PVC) and Polyethylene, which require high processing temperatures. Initially, a gas-filled polymer is formed from which the polymer foam is formed. One example of a typical method of forming a gas-filled polymer relies on the thermal decomposition of chemical blowing agents within a polymer solution, thereby generating nitrogen N₂ or carbon dioxide CO₂ gas in the solution. The thermal decomposition may be caused by the application of heat or as a result of the exothermic heat of reaction during polymerisation.

An alternative method of creating a gas-filled polymer involves the mechanical whipping of gases into a polymer melt, which then hardens either by catalytic action or heat, trapping gas bubbles in a matrix. Low boiling point liquids LBPLs may also be used. Volatilisation of LBPLs e.g. methylene chloride within the polymer melt occurs as a result of the application of heat or the exothermic heat of reaction. Accordingly, gas is introduced into the polymer forming a gas-filled polymer. In one example, gas dissolved in a polymer expands upon reduction of pressure in the system, thereby causing the formation of gas bubbles in the polymer. Alternatively, microspheres may be incorporated into a polymer mass, the spheres consisting of gas-filled polymer that expands upon heating.

In all these cases, after obtaining the gas-filled polymer, typically a foam is then formed using one of three common manufacturing processes: compression moulding, reaction injection moulding or extrusion of the foam.

A problem with these processes is that the temperatures involved can be very high, e.g. in excess of 150°C, as the polymers used are in their molten state. The most common processing method used in creating polymer foam films is extrusion. This is a three stage operation consisting as a first stage of forming a polymer solution with gas dissolved in it. This may be achieved by injection of N₂ or CO₂ into the solution or by the use of blowing agent, to create a single phase solution. Next, nucleation sites are formed, as a result of a rapid pressure drop to create large numbers of uniform sites. Finally, cell growth then takes place by

means of diffusion of the gas to form bubbles. Control of cell growth is achieved by controlling processing conditions such as pressure and temperature.

Methods of forming porous polymer layers have been disclosed such as those disclosed in United States Patent Number 6228476 and United States Patent application number 2001/0021726. Such methods rely on the use of curable polymers.

United States Patent number 3794548 discloses the use of polyurethane in a porous polymer film. Heating of the polymer causes volatilisation of solvents within the polymer resulting in a porous coating.

10 A method of forming a foamed polymer material is required that uses very low processing temperatures in comparison to all traditional methods.

SUMMARY OF THE INVENTION

According to the present invention, there is provided a method of making a material, comprising the steps of:

coating a support with a solution comprising a hydrophilic polymer and a blowing agent; and,

either prior to or after the step of coating said support, interacting with said solution, to cause said blowing agent to generate gas bubbles within the solution causing foaming of said hydrophilic polymer.

20 In one example, the step of interacting with the solution is performed after coating of the support and comprises applying heat to said solution. In this case, heat may be applied to the solution during drying of the coated support.

In an alternative example, the interaction with the solution comprises applying heat to the solution prior to coating of the support such the solution when coated onto the support has bubbles already formed therein. In this case, the heat may be applied by a heater coupled to a vessel holding the solution. Alternatively, heat may be applied by the addition of an acid to the solution to react with the blowing agent to thereby generate bubbles of gas in the solution.

30

ADVANTAGEOUS EFFECT OF THE INVENTION

The present invention provides a method of making a material that enables a polymer foam to be formed without requiring the use of high processing temperatures as required by conventional methods. In particular, in contrast to conventional methods of making foams, a support is coated with a solution of a hydrophilic polymer and a blowing agent. Interaction with the solution either prior to or after the step of coating gives rise to the generation of gas bubbles from the blowing agent which enables a material to be formed at low temperatures. The material has uses in many applications including, amongst others, use as an inkjet medium.

DETAILED DESCRIPTION OF THE INVENTION

The present invention provides a method of making a material, the material having many different possible uses, including amongst others use as an inkjet medium. Initially, in the method of the present invention, a solution is formed of an aqueous polymer together with a blowing agent. The solution is coated onto a support such as resin-coated paper, film base, acetate, polyethylene terephthalate PET, printing plate or any other suitable support. Heat is applied to the solution, either before or after application to the support. The heat causes the blowing agent to decompose and create gas bubbles, thereby forming a polymer foam on the support. The foam is effectively a network of either open- or closed-cell arrangements of voids within a polymer matrix. When dry, the material is suitable for use as an inkjet medium. In particular, the material does not experience the problems associated with conventional porous or non-porous inkjet media.

There are two possible related approaches for forming the material, both of which rely on the formation of a porous hydrophilic polymer layer i.e. a hydrophilic polymer layer with void spaces produced by a generated gas. The gas can be generated either in a coating solution, or during a setting and drying process of the material. In other words, the gas can be generated either before or after the coating of the support.

If the gas is generated before the coating of the support the method involves the coating of a foamed polymer solution. Accordingly, the material is

prepared by coating a support with a layer of foamed polymer solution in which micro-bubbles are formed. The micro-bubbles are formed in an aqueous solution of a hydrophilic polymer and foaming agent. The aqueous solution containing the micro-bubbles is then coated onto a support. The foamed polymer solution is
5 created by heating the solution prior to its application to the support, to promote the decomposition of the blowing agent to generate a gas. Alternatively, an acid may be added to the solution to react with the blowing agent again to generate a gas within the solution. Preferably, a compound which on heating releases an acid, is added to the solution. When the solution is heated, acid is released which
10 reacts with the blowing agent to cause decomposition of the blowing agent and the consequent generation of gas.

If the gas is generated after the coating of the solution, the method involves the coating of a support with an aqueous solution of hydrophilic polymer with a blowing agent followed by the application of heat to the solution i.e. by
15 heating the entire structure of the coated support. The coating is dried, and bubbles are caused to form in the coated layer by heating the layer or the entire coated material to a suitable temperature. In one example, the blowing agent is selected such that heat provided to dry the coated support is sufficient to cause decomposition of the blowing agent and generation of the gas. In an alternative
20 example, a compound which on heating releases an acid, is added to the solution. When the solution is then heated, acid is released which reacts with the blowing agent to cause decomposition of the blowing agent and the consequent generation of gas.

In both approaches described above, any suitable method of coating may
25 be used to coat the solution onto the support. For example, curtain coating, bead coating, air knife coating or any other suitable method may be used. Typically, in bead coating a set-up is used in which a multi-layer arrangement of liquids is applied to a moving web via a hopper. The examples below describe such a set-up.

30 Both the approaches described above create a voided layer, which consists of a hydrophilic polymer e.g. (amongst others) polyvinyl alcohol (PVA), polyethylene oxide (PEO), polyvinylpyrrolidone (PVP), and gelatin. Any suitable

hydrophilic polymer may be used in the method of the present invention. Where the material to be made is intended for use an inkjet medium, the polymer selected must be sufficiently swellable and hydrophilic for the formed material to function as an inkjet medium.

5 Preferably, surfactant may be added to the solution of hydrophilic polymer and blowing agent. The surfactant serves as a coating aid during coating of solution onto the support.

 The blowing agent used in the method of the present invention is selected in dependence on the temperature at which it reacts to generate gas. By selecting
10 a blowing agent that reacts at a relatively low temperature, material may be formed without requiring high temperatures. Examples of suitable blowing agents for use in the method of the present invention, include a mixture of sodium nitrite and ammonium chloride, metal carbonates and bicarbonates. Further examples of suitable blowing agents are described in, for example, the Handbook of Polymeric
15 Foams and Foam Technology, Edited by Daniel Klempner and Kurt C. Frisch, Chapter 17: Blowing Agents for Polymer Foams, Section 3 Chemical Blowing Agents, (Chapter written by Dr. Fyodor A. Shutov).

 In one example of the present invention, three layers of a solution of a polymer are coated simultaneously onto the support. It is possible that the
20 proportion by weight of blowing agent to polymer in the different layers varies and in any one or more of the layers may be up to about 200%. Typically, it would be in an amount from about 10% to about 60%, preferably about 30% to about 50%.

 A surfactant such as a Fluoro-surfactant e.g. Olin 10G, Lodyne S100 or
25 Zonyl FSN, may also be added to the hydrophilic polymer used in the porous hydrophilic polymer layer. The proportion by weight of surfactant, where present, to the weight of each layer of solution as applied to the support may also vary. Typically, it would be in an amount from about 0.01% to about 2.0%, preferably, about 0.01% to about 1.0%. In the case where any number of layer(s) of solution
30 of polymer are coated, the proportions by weight of blowing agent to polymer and surfactant, where present, to solution may have values in the same ranges.

The invention is illustrated by the following examples. Examples 1 and 2 below relate to methods of making a material for use as an inkjet medium although it will be appreciated that the material as manufactured may find uses in any number of other possible applications.

5

EXAMPLES

A material was prepared as follows:

Example 1

10 A resin-coated paper support was coated with three layers. When the material is to be used as an inkjet medium, each of the layers functions as an ink-receiving layer and is therefore referred to as such in the example. Each layer comprised of polyethylene oxide (PEO), blowing agents (a total of 50% by weight compared to the PEO lay-down) and some surfactant.

15 The ink-receiving layer nearest the support consisted of 2.35 g/m² of PEO, 0.66 g/m² of sodium nitrite, 0.51 g/m² of ammonium chloride and 0.212 g/m² of Olin 10G surfactant. The middle ink-receiving layer consisted of 2.55 g/m² of PEO, 0.72 g/m² of sodium nitrite, 0.56 g/m² of ammonium chloride and 0.424 g/m² of Olin 10G surfactant. The top ink-receiving layer consisted of 2.77 g/m² of
20 PEO, 0.78 g/m² of sodium nitrite, 0.61 g/m² of ammonium chloride and 0.636 g/m² of Olin 10G surfactant. The three layers were then coated simultaneously on a bead-coating machine using a standard slide hopper. A control coating was also prepared at the same time where the layers were identical to those described above, except the blowing agents (sodium nitrite and ammonium chloride) were
25 omitted.

To initiate the blowing process, the dryers inside the coating track were set to 70°C through which the coating of this invention was passed.

Example 2

30 A resin-coated paper support was coated with three layers. Again, when the material is to be used as an inkjet medium, each of the layers functions as an ink-receiving layer and is therefore referred to as such in the example. Each layer

comprised of polyvinyl alcohol (PVA), blowing agents (a total of 50% by weight compared to the PVA laydown) and some surfactant.

5 The ink-receiving layer nearest the support consisted of 6.1 g/m² of PVA, 1.72 g/m² of sodium nitrite, 1.33 g/m² of ammonium chloride and 0.212 g/m² of Olin 10G surfactant. The middle ink-receiving layer consisted of 6.8 g/m² of PVA, 1.92 g/m² of sodium nitrite, 1.48 g/m² of ammonium chloride and 0.424 g/m² of Olin 10G surfactant. The top ink-receiving layer consisted of 7.5 g/m² of PVA, 2.11 g/m² of sodium nitrite, 1.64 g/m² of ammonium chloride and 0.636 g/m² of Olin 10G surfactant. The three layers were then coated simultaneously on
10 a bead-coating machine using a standard slide hopper. A control coating was also prepared at the same time where the layers were identical to those described above, except the blowing agents (sodium nitrite and ammonium chloride) were omitted.

To initiate the blowing process, the dryers inside the coating track were set
15 to 90°C through which the coating of this invention was passed.

In both examples a material suitable for use as an inkjet medium was made without the use of high temperatures in the manufacturing process.

CLAIMS:

1. A method of making a material, comprising the steps of:
coating a support with a solution comprising a hydrophilic polymer and a blowing
agent; and,
5 either prior to or after the step of coating said support, interacting with said
solution to cause said blowing agent to generate gas bubbles within the solution,
causing foaming of said hydrophilic polymer.
2. A method according to claim 1, in which the step of interacting with the
10 solution is performed after coating of the support and comprises applying heat to
said solution.
3. A method according to claim 2, in which heat is applied to the solution
during drying of the coated support.
15
4. A method according to claim 1, in which the hydrophilic polymer is a
polymer selected from the group consisting of polyvinyl alcohol, polyethylene
oxide, polyvinylpyrrolidone and gelatin.
- 20 5. A method according to claim 1, in which a plurality of layers of coating
solution are coated simultaneously onto said support.
6. A method according to claim 1, in which a surfactant is included in the
solution of hydrophilic polymer and blowing agent.
25
7. A method according to claim 6, in which the surfactant is a flouro-
surfactant.
8. A method according to claim 6, in which the proportion by weight of
30 surfactant to the solution is in an amount from about 0.01% to about 2.0%,
preferably, about 0.01% to about 1.0%.

9. A method according to claim 1, in which the proportion by weight of blowing agent to polymer is in an amount up to about 200%.

10. A method according to claim 9, in which the proportion by weight of blowing agent to polymer is in an amount from about 10% to about 60%, preferably, about 30% to about 50%.

11. A method according to claim 1, in which the interaction with the solution comprises applying heat to the solution.

10

12. A method according to claim 11, in which heat is applied to the solution prior to coating of the support such the solution when coated onto the support has bubbles already formed therein.

15 13. A method according to claim 12, in which the heat is applied by the addition of an acid to said solution to react with the blowing agent to thereby generate bubbles of gas in the solution.

20 14. A method according to claim 11, in which a compound which on heating releases an acid is added to the solution, such that when the solution is heated, acid is released which reacts with the blowing agent to cause decomposition of the blowing agent.

25 15. A method according to claim 1, in which the material is an inkjet medium.

ABSTRACT

The invention provides a method of making a material. The method
5 comprises the step of coating a support with a solution comprising a hydrophilic
polymer and a blowing agent. Either prior to or after the step of coating the
support, the solution is interacted with in some way e.g. heated, to cause the
blowing agent to generate gas bubbles within the solution, causing foaming of the
hydrophilic polymer.

10

